



38 Polskie Seminarium Anihilacji Pozytonów

38th Polish Seminar on Positron Annihilation

PROGRAM I STRESZCZENIA WYSTĄPIEŃ

Kazimierz Dolny

08-12 czerwca 2009

www.fizyka.umcs.lublin.pl/PSPA09/PSPA09.html

ORGANIZATORZY



Zakład Metod Jądrowych Instytutu Fizyki
Uniwersytetu Marii Curie – Skłodowskiej

Instytut Fizyki Doświadczalnej
Uniwersytetu Wrocławskiego

KOMITET ORGANIZACYJNY

Bożena Jasińska
Przewodnicząca Komitetu Organizacyjnego

Jan Chojcan
Wiceprzewodniczący Komitetu Organizacyjnego

Tomasz Goworek
Doradca

Bożena Zgardzińska
Sekretarz

Radosław Zaleski
Redaktor materiałów konferencyjnych w Nukleonice

Mieczysław Budzyński
Członek Komitetu

Jan Wawryszczuk
Członek Komitetu

Marek Wiertel
Członek Komitetu

Zbigniew Surowiec
Członek Komitetu

Marek Pietrow
administracja strony www

POSITRON ANNIHILATION STUDY OF NANOSTRUCTURED ZrO₂

J. D. Fidelus¹, S. Mariazzi², R. S. Brusa², A. Karbowski³, G. Karwasz³

¹*Instytut Wysokich Ciśnień PAN, ul. Sokołowska 29/37, 01-142 Warszawa, Polska*

²*Dipartimento di Fisica, Università di Trento, via Sommarive 14, I-38100 Povo (Trento), Italy*

³*Instytut Fizyki, Uniwersytet Mikołaja Kopernika, ul. Grudziądzka 5, 87-100 Toruń, Polska*

The stabilized zirconia alloys have interesting mechanical and ionic properties which make possible to use it as structural and wear components, oxygen gas sensors, fuel cells etc.

In present work, Doppler broadening depth-resolved positron annihilation spectroscopy [1] was performed on pure zirconia nanopowders sintered in oxygen atmosphere. Zirconia nanopowders were grown by a hydrothermal microwave-driven process followed by annealing. To produce the mixture of tetragonal and monoclinic zirconia polymorphs, the obtained powder was annealed at 700 °C, a temperature found to be optimal from the point of view of the grain size and crystal structure (tetragonal one remains after cooling). In order to obtain monoclinic ZrO₂ nanopowder, the thermal treatment was conducted at 800 °C. Physical properties of obtained nanopowders (exhibiting the grain size of 20 to 40 nm, after annealing at 700-800 °C temperature, respectively) differ from those of bulk ZrO₂ due to, in particular, a large surface area.

Doppler-broadening spectra show low values of the normalized [1] S-parameter, varying little with the depth, from 0,495 on the surface to 0,47-0,49 in bulk. The higher annealing temperature and oxygen concentrations lead to lower bulk S-values. We studied also the positronium fraction from the 3- γ annihilation signal. Ortho-positronium fraction is about 10-11% for all samples on the surface, down to 7-8% in the bulk for samples annealed at 700 °C and 5-6% for samples annealed at 800 °C. Presence of ortho-positronium in nanopowders of ZrO₂ is also supported by lifetime measurement by Procházka et al. [2] who observed a long (34 ns) lifetime component with 6.4-7.4% intensity in similar samples.

This work was partially supported by grant no. N N508 0851 33 of Ministry of Science and Higher Education (Poland) donated for the years 2007-2009 and by UMK Rector grant No 524-F.

[1] R.S. Brusa, G.P. Karwasz, M. Bettonte, A.Zecca, *Applied Surface Science* **116**, 59 (1997).

[2] I. Procházka, J. Čížek, J. Kuriplach, O. Melikhova, T.E. Konstantinova, I.A. Danilenko, *Acta Phys. Polon.* **113** (5), 1495 (2008).