



Imaging and spectral information with time-domain OCT Application to works of art

Gaël Latour

Institut des Nanosciences de Paris (INSP)

gael.latour@insp.jussieu.fr

Latour *et al.*, Applied Optics, *in submission*

OCT4ART – Torun, Poland – 3-5 July 2008


Optical techniques to study works of art

Purpose: obtaining information from the studied work of art

- ✓ Pigment
- ✓ Dye
- ✓ Varnish
- ✓ Surface state
- ✓ Number of layers
- ✓ Thickness of a layer
- ...

Interest of the optical techniques:


non destructive and without any contact analysis



Time-domain OCT: imaging and spectral information


Overview

- ✓ Setup
- ✓ Acquisition and processing
 - ✓ Imaging: painting
 - ✓ Imaging: music instruments
 - ✓ Spectral information




Setup


Michelson interferometer





Equal optical paths

→ Interference pattern






Setup Setup at the INSP



interferometric objective




- ✓ Sensitive in the visible range
- ✓ Stability of the device



Time-domain OCT: imaging and spectral information


Overview

- ✓ Setup
- ✓ Acquisition and processing
 - ✓ Imaging: painting
 - ✓ Imaging: music instruments
 - ✓ Spectral information




Acquisition and processing


Acquisition






For each position of the objective, one image is recorded

$$\Delta z \sim 30 \text{ nm}$$





Acquisition and processing Imaging






Time-domain OCT: imaging and spectral information


Overview

- ✓ Setup
- ✓ Acquisition and processing
 - ✓ Imaging: painting
 - ✓ Imaging: music instruments
 - ✓ Spectral information




Imaging: painting

Imaging: one pictorial layer




From axial slices, reconstruction of 3D imaging






Imaging: painting

Imaging: stratified layers






Imaging: painting

Imaging: varnished paint layer



Varnish

Viridian green



Interface air/varnish


Varnish

Interface varnish/paint


Painting

300 μm

3D Images



OCT4ART



Gaël Latour



Time-domain OCT: imaging and spectral information

Overview


- ✓ Setup
- ✓ Acquisition and processing
 - ✓ Imaging: painting
- ✓ Imaging: music instruments
 - ✓ Spectral information



Imaging: music instruments

Wood instruments: violin, cello...

Precious and delicate objects



Stratified layers?

Presence of pigments?


Interface varnish / wood?



Imaging: Music instruments

OCT: device for the study of music instruments?

Interest of OCT?



Instruments

Collaborations

Music Museum Laboratory

Jean-Philippe Echard

Stéphane Vaiedelich

(*Cité de la Musique, Paris*)

Conservator and violin maker

Balthazar Soulier

(*Staatliche Akademie der Bildenden
Künste, Stuttgart*)



Imaging: Music instruments Wood

*Among the wood species:
choice of maple*

Back, headpiece and rib



OCT4ART – July 2008







Landolfi, Milan, XVIIIth (private collection)

Gaël Latour





Imaging: Music instruments Wood: maple






Imaging: Music instruments Wood + under layer + varnish



→ interface between varnish and under layer



OCT: imaging




Painting



Music instruments

and ...


- Number of layers
- Thicknesses
- Surface state
- Presence of fillers
- Informations about the wood



Time-domain OCT: imaging and spectral information

Overview

- ✓ Setup
- ✓ Acquisition and processing
 - ✓ Imaging: painting
 - ✓ Imaging: music instruments
 - ✓ Spectral information




Spectral information from OCT Spectral information




Glass

Interferogram



Fourier Transform




Spectral transfer function of the device


Central wavelength $\sim 620 \text{ nm}$

Spectral width $\sim 150 \text{ nm}$

Spectral resolution: 2 to 5 nm






Spectral information from OCT Spectral information: dye




Red dye on glass

Raw data



Reproducible spectra






Spectral information from OCT

Spectral information: pictorial layer


Diffusing medium

Spectra obtained after FT

Spectra of several pigments



Chrome yellow
painting



Spectra from several pigments are different


Outlook:



Obtaining reproducible spectra

oct → Identification

→ Outlook



OCT applied to works of art




➤ *Time-domain OCT*

- ➡ Axial resolution: 1,5 µm
- ➡ Sensitive in the visible range



➤ *3D Imaging*



- ➡ Thickness of a varnish
- ➡ Thicknesses of layers
- ➡ Presence of fillers
- ➡ ...

➤ *Spectral information*

- ➡ Validation on dyes

➤ *Outlook*


- ➡ Spectral information on pigments

Acknowledgements:

Isabelle Emond (INSP),

Jean-Philippe Echard and Stéphane Vaiedelich (Cité de la Musique, Paris)

Balthazar Soulier (SABK, Stuttgart)



Thank you for your attention ...